

Cutech Alloys Private Limited

FEDER ALLOYS

Copper Alloys	Cu	Sn	Pb	Zn	Fe	Ni	P	Al	Mn	Si	Sb	S	Bi
C89320	87-91	5-7	0.09	1	0.20	1	0.30	0.005	-	0.005	0.35	0.08	4-6
C89325	84-88	9-11	0.1	1	0.15	1	0.1	0.005	-	0.005	0.50	0.08	2.7-3.7
C89510	86-88	04-6	0.25	4-6	0.20	1	0.05	0.005	-	0.005	0.25	0.08	0.5-1.5
C89520	85-87	5-6	0.25	4-6	0.20	1	0.05	0.005	-	0.005	0.25	0.08	1.6-2.2
C89530	84-89	3.5-6	0.2	7-9	0.3	1	0.05	0.01	-	0.01	0.20	-	1-2
C89831	87-91	2.7-3.7	0.1	2-4	0.3	1	0.05	0.005	-	0.005	0.25	0.08	2.7-3.7
C89833	87-91	4-6	0.1	2-4	0.3	1	0.05	0.005	-	0.005	0.25	0.08	1.7-2.7
C89835	85-89	6-7.5	0.1	2-4	0.2	1	0.1	0.005	-	0.005	0.35	0.08	1.7-2.7
C89836	87-91	4-7	0.25	2-4	0.35	0.9	0.06	0.005	-	0.005	0.25	0.08	1-5-35
C89837	84-88	3-4	0.1	6-10	0.3	1	0.05	0.005	-	0.005	0.25	0.08	0.7-1.2
C89844	83-86	3-5	0.2	7-10	0.3	1	0.05	0.005	-	0.005	0.25	0.08	2-4
C89940	64-68	3-5	0.01	3-5	0.7-2	20-23	0.1-0.15	0.005	-	0.15	0.20	0.05	4-5.5

Cutech

RECYCLED TO PERFECTION